

BRUSHABLE CERAMIC RED/BLUE

PRODUCT INFORMATION

	<table> <tr> <th>Stock No.</th><th>Package Size</th></tr> <tr> <td>11752</td><td>Red 500g</td></tr> <tr> <td>11762</td><td>Blue 500g</td></tr> </table>	Stock No.	Package Size	11752	Red 500g	11762	Blue 500g
Stock No.	Package Size						
11752	Red 500g						
11762	Blue 500g						
Description	A high performance, high density, ceramic filled, brushable epoxy to seal and protect new or repaired surfaces from cavitation, pitting, erosion and wear						
Recommended Applications	<ul style="list-style-type: none"> Seal and protect new equipment exposed to erosion and corrosion Protect pump casings, impeller blades, gate valves, water boxes and fan blades Rebuild heat exchangers, tube sheets and other circulation water equipment Use it as a topcoat on repaired surfaces to provide an exceptionally smooth surface 						

PRODUCT DATA

Typical Physical Properties	Colour	Red or Blue		
	Mix Ratio by Volume	3.4 : 1		
	Mix Ratio by Weight	5.6 : 1		
	% Solids by Volume	100		
	Pot life at 25°C/ mins	40		
	Specific Volume CC/Kg	633		
	Cured Shrinkage cm/cm	0.002		
	Density g/cm ³	1.58		
	Temperature resistance / °C	Wet 65°C Dry 175°C		
	Coverage	0.633m ² /Kg @ 1mm		
	Cured Hardness / Shore D	90		
	Dielectric Strength KV/mm	15		
	Adhesive Tensile Shear / MPa	13.75		
	Compressive Strength MPa	105		
	Coefficient of Thermal Expansion x10 ⁻⁶ cm/cm/°C	34		
	Thickness per Coat / mm	0.25-0.5		
	Functional Cure Time /Hours	24		
Recoat Time /Hours	4-6			
Mixed Viscosity /cps (where applicable)	32000			
Chemical Resistance	7 days room temperature cure (30 days) - Testing carried out 30 days immersion at 24 °C			
	Ammonia	Very Good	Methylene Chloride	Poor
	Cutting Oil	Excellent	Sodium Hypochlorite 5% (Bleach)	Very Good
	Ethyl Alcohol	Excellent	Sodium Hydroxide 10%	Excellent
	Gasoline (Unleaded)	Excellent	Sulphuric Acid 10%	Excellent
	Hydrochloric Acid 10%	Excellent	Xylene	Fair
	Methyl ethyl Ketone (MEK)	Poor		
Excellent = +/- 1% weight change				
Very Good = +/- 1-10% weight change				
Fair = +/- 10-20% weight change				
Poor = > 20% weight change				



BIGA GROUP

SPECIAL WELDING, SHIP / OFF SHORE / INDUSTRY SERVICE
ENGINEERING, CONSULTING AND SURVEY
www.bigagroup.com

Brushable Ceramic Red/Blue

APPLICATION INFORMATION

Cure	Working time is 40 minutes at 22°C. Brushable Ceramic will achieve a tack-free finish approximately 2-3 hours after applying. Functional cure is achieved in about 24 hours at 22°C. Cure may be accelerated by using heat after the coating has been allowed to harden under ambient conditions. Material will fully cure at 65°C in 4 hours. Remember the maximum re-coat time between coats is 4-6 hours. Each coat should be 0.5-1.0mm per coat. Two coats insure a pinhole free lining.
Surface Preparation	<p>Proper surface preparation is essential to a successful application. The following procedures should be considered :</p> <ul style="list-style-type: none"> • All surfaces must be dry, clean and rough. • If surface is oily or greasy, use MEK, Acetone, IPA or similar to degrease the surface. • All surfaces must be roughened, ideally by grit blasting (3-16 mesh/cm grit size) or by grinding with a coarse wheel or disc. This creates increased surface area and "edges" to lock into, and essential for successful application. • Metal that has been handling sea water or other salt solutions should be grit blasted and high pressure water blasted and left overnight to allow any salts in the metal to 'sweat' to the surface. Repeat blasting may be required to 'sweat out' all the soluble salts. A test for chloride contamination should be performed prior to any epoxy application. The maximum soluble salts left on the substrate should be no more than 40 p.p.m. (parts per million). • Chemical cleaning with MEK, Acetone, IPA or similar should follow all abrasive preparation. This will help to remove all traces of sandblasting, grit, oil, grease, dust or other foreign substances. • Heating the repair area to 30°C - 40°C immediately before applying Brushable Ceramic is recommended. This procedure dries off any moisture, contamination or solvents and assists the Ceramic System in achieving maximum adhesion to the substrate.
Mixing	Brushable Ceramic is formulated to brush easily onto prepared surfaces with a short bristle brush. Add hardener to resin and mix thoroughly with a spatula or similar tool until a uniform, streak-free consistency is obtained, this should take about 4 minutes. Be sure to mix material from the bottom and sides of container. It is strongly recommended that full container units be mixed
Application	For best results, product should be kept and applied at room temperature. Brushable Ceramic can be applied when temperatures are between 15°C and 30°C. When temperatures are below 22°C, cure and pot life will be longer, and above room temperature cure and pot life will be shorter.
Shelf life & Storage	A shelf life of 3 years from date of manufacture can be expected when stored at room temperature (22°C) in their original containers
Precaution	For complete safety and handling information, please refer to Material Safety Data Sheets prior to using this product.
Warranty	ITW Devcon will replace any material found to be defective. As the storage, handling and application of this material is beyond our control we can accept no liability for the results obtained.
Disclaimer	<p>All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Devcon makes no representations or warranties of any kind concerning this data.</p> <p>For product information visit www.bigagroup.com / www.devconeurope.com alternatively for technical assistance please call +385 52 880 882 or send an e-mail to biga@biga.hr.</p>



BIGA GROUP

SPECIAL WELDING, SHIP / OFF SHORE / INDUSTRY SERVICE
ENGINEERING, CONSULTING AND SURVEY
www.bigagroup.com